



Porotherm Application Guide

Topic: Best Practices of Porotherm Plus
End Bricks Application

Application Areas:

- Porotherm VP End Bricks are recommended to be used along with Porotherm HP (Horizontally perforated)
- VP End Bricks are ideal for wall junctions and door window jambs



Application Areas of Porotherm VP

Advantages of using End Bricks

- Uniform Clay Surface all across to ensures strong and uniform bonding
- Strong door and window jambs
- High compressive strength
- Easy for anchor installation



Porotherm VP Parameters

Product Names	Dimension in mm			Weight (Kg)	Density (Kg/m ³)	Water Absorption (%)	Efflorescence	Fire Resistance
	Length	Width	Height					
Porotherm VP 200	400	200	200	11.300	710 to 840	≤20	Slight	240
Porotherm VP 150	400	150	200	8.600				120
Porotherm VP 100	400	100	200	6.700				90